



MAXSHEEN[®] POOL

DECORATIVE ACRYLIC COATING FOR SWIMMING POOLS

DESCRIPTION

MAXSHEEN POOL is a high quality water-based acrylic coating, resistant to UV-rays, and designed for decorative finish of swimming pools.

APPLICATION FIELDS

MAXSHEEN POOL is applied on concrete floors, cement mortars, etc. Generally, it is applied on building materials used in the production of swimming pools, fountains and dams reservoirs.

ADVANTAGES

- It withstands permanent contact with water.
- It is non-toxic and solvent-free. Environmentally friendly.
- Application temperature between 5 °C minimum and 40 °C maximum.
- MAXSHEEN POOL is fungicide and bactericidal, thus formation of algae, fungus, lichen, etc is highly inhibited.
- Protects against carbon dioxide, chloride ions penetration and water.
- Easy cleaning only with water.

APPLICATION INSTRUCTIONS

Surface preparation

The surface to be coated must be free from dirt, grease, etc. Badly adhered paint must be completely eliminated with sandpaper or using MAXCLEAN-R (Technical Bulletin N°.: 86). Allow 28 days of curing time for new concrete.

Application

Stir paint previous to application. MAXSHEEN POOL can be applied by brush, spray or roller. Apply a first coat diluting 4 parts of MAXSHEEN POOL with 1 part of water. Allow at least 4-5 hours curing. Apply a second coat without diluting.

Application conditions

Do not apply below 5 °C or if lower temperature is expected 24 hours after application. Do not apply if rain is expected.

Curing

Proper curing time before water filling are 7 days at 20 °C and 50 % relative humidity. Lower temperatures and higher R.H. increase curing time.

Cleaning

Clean tools and equipment with water immediately after use. Once the product dries, only can be removed by mechanical methods.

CONSUMPTION

3 - 4 m²/Kg. in total of two coats, depending on the absorption rate and conditions of the surface to be treated.

TECHNICAL DATA

Appearance	Homogeneous paste
Density (Kg/dm³)	1,15
Solids content (%)	76
Adhesion on concrete (MPa)	> 2,5
Touch curing at 20 °C (hours)	1
Curing time for water immersion (days) at 20 °C and 50 % R.H.	7

COLOURS

It is available in white, blue and dark blue colour.

PACKAGING

MAXSHEEN POOL is supplied in 5 and 25 kg. drums.

STORAGE

Twelve months in its original unopened packaging, protected from frost in a dry covered place with temperatures above 5 °C.

SAFETY AND HEALTH

MAXSHEEN POOL is non-toxic, but skin and eye contact must be avoided. Safety goggles and protective gloves should be used during the application. In case of skin contact, wash affected areas with soap and water. In case of eye contact rinse thoroughly with clean water but do not rub. If irritation continues, seek medical attention.

Safety Data Sheet for MAXSHEEN POOL is available by request.

Final user must do disposal of the product and its empty packaging according to official regulations.

GUARANTEE

The information contained in this leaflet is based on our experience and technical knowledge, obtained through laboratory testing and from bibliographic material. DRIZORO reserves the right to introduce changes without prior notice. Any use of this data beyond the purposes expressly specified in the leaflet will not be the Company's responsibility unless authorised by us. We shall not accept responsibility exceeding the value of the purchased product.



DRIZORO, S.A.

C/ Primavera 50-52 Parque Industrial Las Monjas
28850 TORREJON DE ARDOZ – MADRID (SPAIN)
Tel. 91 676 66 76 - 91 677 61 75 Fax. 91 675 78 13
e-mail: info@drizoro.com Web site: drizoro.com

